

**DEQING TO****TONGCHEM INDUSTRY****TECHNICAL DATA SHEET**

Iron Oxide Red

Appearance	Red pigment
Delivery Form	Powder
Chemical Class	Synthetic iron oxide alpha-Fe ₂ O ₃
Color Index	Pigment red 101(77491)
CAS No.	1309-37-1
Use Recommendation	Coatings, Construction, plastic, Rubber, etc

TECHNICAL DATA		
Item	Specification	Test Method
Color Shade (ΔE) max	1.0	ISO787-1
Tinting Strength %	95-105	ISO787-24
Water-Soluble Content [%] max	0.5	DIN EN ISO787 Part 3 (1995)
Sieve Residue (0.045mm) [%] max	0.3	DIN EN ISO787 Part 2 (1995)
PH Value	3.0 ----7.0	DIN EN ISO787 Part 9 (1995)
Fe ₂ O ₃ [%] min	95.0	DIN 55913 Sheet 2 (1972)
Moisture (After Production) [%] max	1.0	DIN EN ISO 787 Part 2 (1995)
Oil Absorption [g/100g]	15-25	DIN EN ISO787 Part 5 (1995)

STANDARD PACKAGING	25kg/bag with pallet, wrapped and shrinked 1000kgs/1100kgs jumbo bags with pallet
TRANSPORT AND STORAGE	
Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.	
SAFETY	
The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured. The information contained in the safety data sheet should be observed. This contains information on handling, product safety and ecology.	

This information is given in good faith, without warranty. It also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.