

| Count | PVA YARN 80S/1 AT 90 DEGREE |
|----------------------------------|-----------------------------|
| Initial dissolution temperature | 85 degree |
| Complete dissolution temperature | 98 degree |
| Breaking Strength | 26.45 |
| Strength | 195.20 |
| Evenness | 15.68 |
| Cv% | 16.82 |
| U% | 12.95 |
| Thin-50%/km | 60 |
| Thick+50%/km | 225 |
| Nep +200%/km | 370 |
| Hairiness | 3.74 |

ANHUI WANWEI UPDATED HIGH-TECH MATERIAL INDUSTRY COMPANY LIMITED

Add: No.56 Chaowei Road Chaohu city. Anhui.China

Tel: +86-551-82189233

Fax: +86-551-82317233

E-mail: JCKB2@126.com

p.c:238002