# 洛阳市三诺化工有限公司

### LUOYANG SANNUO CHEMICAL CO.,LTD.

East section of Century Avenue, Jili District, Luoyang City, Henan, China

T: (00)86-379-67518785

F: (00)86-379-67510168

E: sannuo@sannuogroup.cn

Http://www.sannuogroup.cn

## Technical data sheet

Trioctyl Phosphate(TOP)

■CAS No: 78-42-2

■Molecular formula: C<sub>24</sub>H<sub>51</sub>O<sub>4</sub>P

■ Molecular weight: 434.64 (International Atomic Weight Table,1987)

■Molecular structure:

■Properties:transparent oily liquid,b.p.216°C (4mmHg).

**■**Uses:

- (1) It is now chiefly used as a processing solvent, instead of hydroterpineol, for producing hydrogen peroxide by anthraquinone process. It is an ideal solvent in this process, for its low volatility and good extraction distribution coefficient.
- (2) It is also a cold-resisting and fire-retarding plasticizer applied in ethylenic and cellulosic resins, synthetic rubbers. The cold resisting property is superior to adipate esters.
- ■Package:180kg /iron drum net each,1000L/IBC drum.

### ■Storage and transportation:

Stored at dry, shady, ventilated place. Prevented from collision and sunrays, rain-attack during handling and shipping.

Met the high hot and clear fire or contact the oxidizing agent, caused the burning danger.

#### **■Quality index:**

Item	Premium grade	Industrial Grade
Appearance	Transparent, oily liquid with no visible impurities	
Content (GC),%	≥99.0	≥99.0
Dioctyl phosphate content (GC),%	≤0.1	≤0.2
Octanol content (GC),%	≤0.1	≤0.15
Surface tension,mN/m (20∼25℃)	≥18	≥18
Acid value,mgKOH/g	≤0.1	≤0.2

Colourity (Pt-Co)	≤20	≤30
Density,g/mL	0.921~0.927	0.921~0.927
Water content,%	≤0.1	≤0.2
Viscosity (cp)25℃mm²/s	≤14	≤20

