

Count	PVA YARN 80S/1 AT 90 DEGREE
Initial dissolution temperature	85 degree
Complete dissolution temperature	98 degree
Breaking Strength	26.45
Strength	195.20
Evenness	15.68
Cv%	16.82
U%	12.95
Thin-50%/km	60
Thick+50%/km	225
Nep +200%/km	370
Hairiness	3.74

ANHUI WANWEI UPDATED HIGH-TECH MATERIAL INDUSTRY COMPANY LIMITED

Add: No.56 Chaowei Road Chaohu city. Anhui.China

Tel: +86-551-82189233

Fax: +86-551-82317233

E-mail: JCKB2@126.com

p.c:238002