

Count	PVA YARN 80S/1 AT 90 DEGREE
Initial dissolution temperature	85 degree
Complete dissolution temperature	98 degree
Breaking Strength	26.45
Strength	195.20
Evenness	15.68
Cv%	16.82
U%	12.95
Thin-50%/km	60
Thick+50%/km	225
Nep +200%/km	370
Hairiness	3.74

**ANHUI WANWEI UPDATED HIGH-TECH MATERIAL INDUSTRY COMPANY LIMITED**

**Add: No.56 Chaowei Road Chaohu city. Anhui.China**

**Tel: +86-551-82189233**

**Fax: +86-551-82317233**

**E-mail: [JCKB2@126.com](mailto:JCKB2@126.com)**

**p.c:238002**